

## RAWCELL® Fiber - NETPLUS (6,35/15)(0,1-0,1)S(13)

### Description of the product

NETPLUS is a sandwich panel without a cosmetic finish, with an aluminium honeycomb core and glass fibre mesh skins. Main fields of application: furniture, weight-reduction of marble and mosaics.

#### Layers

##### 1) INTERNAL CORE


aluminium honeycomb  
(Starcell production)  
aluminium alloy: 3003-3105 series  
density: 29 - 50 - 56 - 65 kg/m<sup>3</sup>  
cell diameter:  
6.35 mm (standard);  
10 - 12.7 - 19 mm (on request)

##### 2) ADHESIVE

thermosetting  
(Starcell formula)

##### 3) EXTERNAL SKIN

glass fibre mesh  
(weight of the mesh: 60-100 g/m<sup>2</sup> per side)



### Technical sheet of the panel

#### PRODUCT ID CODE

Code structure	Value in this sheet	Meaning
RAWCELL®		family to which the product belongs
Fiber		subfamily to which the product belongs
NETPLUS (n/n)(n-n)		panel type
NETPLUS (n/ )( )	6,35/ =	size (mm) of the hexagonal honeycomb cell
NETPLUS ( /n)( )	/15 =	panel thickness (mm)
NETPLUS ( / )(n-n)	0,1-0,1	thickness (mm) of the two skins
S(n)	13=	standard dimensions (mm) - S(13) = 1.550 X 3.050

## CHARACTERISTICS OF MATERIALS AND COMPONENTS

### Structural skins

material:	glass fibre mesh
standard thicknesses (mm):	0,1
surface appearance:	raw
standard adhesive:	thermosetting system (Starcell formula)

### Hexagonal cell honeycomb

material:	aluminium foil
type:	alloy series 3003 - 3105
foil thicknesses (µm):	60 - 70
density (kg/m <sup>3</sup> ):	29 - 50 - 56 - 65
standard cell sizes (mm):	6,35
on request cell size (mm):	10 - 12,7 - 19

## PHYSICAL AND DIMENSIONAL CHARACTERISTICS OF THE PANEL

### Dimensions

standard (mm):	S(11) = 1.300 X 3.050 - S(13) = 1.550 X 3.050
special (mm):	1.300 - maximum length: 4.300

### Thicknesses

standard (mm):	5	10	12,7	15	20	25	30
special (mm):	from 5 to 75						
tolerance (mm):	± 0,3						

### Weights\*

weights referred to standard thicknesses (kg/m <sup>2</sup> ):	1,21	1,54	1,71	1,86	2,19	2,51	2,84
tolerance (kg/m <sup>2</sup> ):	± 0,2						

\*The weights refer to panels with the following characteristics:

cell size (mm): 6,35

foil thickness (µm): --

thickness of the skins (mm): 0,1

## MECHANICAL CHARACTERISTICS OF THE PANEL

The characteristics of this sheet refer to the following type of panel:

RAWCELL® Fiber - NETPLUS (6,35/15)(0,1-0,1)S(13)

Starcell's Technical Department will gladly work with customers to determine the features of other panel configurations

Type	Standard	Characteristic value						
standard thicknesses	-	5	10	12,7	15	20	25	30
maximum load* (N):	DIN 53293; EN 14125				121			
deflection at Max* load (mm):	DIN 53293; EN 14125				10,69			
resistance to peeling* (N):	DIN 53295	80						
compressive strength* (Kg/cm <sup>2</sup> ):	UNI 4913	18						
elasticity modulus (E)* (N/mm <sup>2</sup> ):	DIN 53293				2.843			
stiffness modulus (R)* (N/m <sup>2</sup> ):	DIN 53293	5						
operating temperature (°C):		from -40°C to +80°C						

(\* ) values obtained by Starcell's Internal Laboratory.

## PROPERTIES

- Good resistance to shear and bending stresses.
- Good dimensional stability and flatness.
- Very good compressive strength (due to aluminium honeycomb).
- Maximum mechanical performance, compared to the high lightness of the panel.
- Excellent weather resistance.
- Particularly low price for this product category.
- Wide operating temperature range.

## FIELDS OF APPLICATION

The typical applications of the RAWCELL® Fiber - NETPLUS panel concern the marble, stone, ceramic and, above all, mosaic market, where high mechanical properties are required together with overall moderate weights to simplify the handling of the finished product; the panel is also used in the furniture industry, in particular to produce high-end doors or up-and-over doors; it is supplied in standard or custom sizes to suit all needs.

## STORAGE

The RAWCELL® Fiber - NETPLUS panel is a product in the "semi-finished products" category and therefore is subject to further processing; we recommend storing the panels horizontally in a closed and dry environment, possibly away from heat sources and to support them along their edges.

## SAFETY DATA SHEETS

On request, safety data sheets for this product are available in Italian or English. For more information, please visit: [www.starcellspa.com](http://www.starcellspa.com).

*Scheda tecnica aggiornata al 07-09-2019*